



TEST REPORT

DATE: 10-29-2013 TEST NUMBER: 0400143

CLIENT Tile Tech Pavers

TEST CONDUCTED Surface Flammability of Carpets and Rugs (16 CFR Chapter II, Subchapter D, Part 1630 CPSC FF-170) also referenced as ASTM D2859



PRODUCT	Tour Putt Nylon
DESCRIPTION	80035883 Turf
REFERENCE	WR #13341

TEST CRITERION

The uncharred area of the test specimen must be greater than one inch in at least seven of the eight specimens tested in order to meet the acceptance criterion.


TEST RESULTS

	SPECIMEN NUMBER							
	1	2	3	4	5	6	7	8
Uncharred Area (Inches)	3.6	3.5	3.4	3.3	3.6	3.6	3.5	3.4

NOTE: This Sample was tested on the face side.

This sample **PASSES** the Federal Flammability Standard DOC FF 1-70

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.



DATE: 02-15-2019	TEST NUMBER: 0403748
CLIENT	TenCate Turf Systems
TEST CONDUCTED	Surface Flammability of Carpets and Rugs (16 CFR Chapter II, Subchapter D, Part 1630 CPSC FF-170) also referenced as ASTM D2859
PRODUCT NAME	2161 Everglade Spring
DESCRIPTION OF PRODUCT TESTED	Turf 1763302-B13-2

TEST CRITERION


The uncharred area of the test specimen must be greater than one inch in at least seven of the eight specimens tested in order to meet the acceptance criterion.

TEST RESULTS

	SPECIMEN NUMBER							
	1	2	3	4	5	6	7	8
Uncharred Area (Inches)	2.6	0.6	2.8	3.2	2.2	2.5	3.0	3.1

NOTE: This Sample was tested on the face side.

This sample **[PASSES]** the Federal Flammability Standard DOC FF 1-70

APPROVED BY: 

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us



DATE: 02-15-2019 TEST NUMBER: 0403749

CLIENT TenCate Turf Systems

TEST CONDUCTED Surface Flammability of Carpets and Rugs (16 CFR Chapter II, Subchapter D, Part 1630 CPSC FF-170) also referenced as ASTM D2859

PRODUCT NAME 2187 Everglade Spring Pro

DESCRIPTION OF PRODUCT TESTED Turf
0143681002-F063-3

TEST CRITERION

The uncharred area of the test specimen must be greater than one inch in at least seven of the eight specimens tested in order to meet the acceptance criterion.


TEST RESULTS

	SPECIMEN NUMBER							
	1	2	3	4	5	6	7	8
Uncharred Area (Inches)	2.7	3.0	2.8	2.5	3.1	2.6	2.7	3.0

NOTE: This Sample was tested on the face side.

This sample **[PASSES]** the Federal Flammability Standard DOC FF 1-70

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.



DATE: 02-15-2019 TEST NUMBER: 0403750

CLIENT TenCate Turf Systems

TEST CONDUCTED Surface Flammability of Carpets and Rugs (16 CFR Chapter II, Subchapter D, Part 1630 CPSC FF-170) also referenced as ASTM D2859

PRODUCT NAME 2175 Pet Turf
DESCRIPTION OF PRODUCT TESTED Turf
1751102-B18-2

TEST CRITERION

The uncharred area of the test specimen must be greater than one inch in at least seven of the eight specimens tested in order to meet the acceptance criterion.


TEST RESULTS

	SPECIMEN NUMBER							
	1	2	3	4	5	6	7	8
Uncharred Area (Inches)	3.2	3.1	3.0	2.7	3.2	3.1	3.2	3.2

NOTE: This Sample was tested on the face side.

This sample **PASSES** the Federal Flammability Standard DOC FF 1-70

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.